

**Table 110FW.E3.1A
(Series 110FW)
Mechanical Specifications**

Temp (F)	Pipe Strengths (psi)					Pipe Moduli (psi)				
	Axial Tensile	Hoop Tensile	Axial Flex.	Hoop Flex.	Axial Comp.	Axial Tensile	Hoop Tensile	Axial Flex.	Hoop Flex.	Axial Comp.
Ambient	8,400	26,400	16,800	N/A	18,000	1,400,000	2,200,000	1,400,000	2,200,000	1,500,000
150	8,400	26,400	16,800	N/A	18,000	1,400,000	2,200,000	1,400,000	2,200,000	1,500,000
175	8,190	25,740	16,380	N/A	17,550	1,365,000	2,145,000	1,365,000	2,145,000	1,462,500
200	7,980	25,080	15,960	N/A	17,100	1,330,000	2,090,000	1,330,000	2,090,000	1,425,000
225	7,770	24,420	15,540	N/A	16,650	1,295,000	2,035,000	1,295,000	2,035,000	1,387,500
250	7,560	23,760	15,120	N/A	16,200	1,260,000	1,980,000	1,260,000	1,980,000	1,350,000

ASTM D4024 / D5421 Flange Codes

2" - 6" Flanges, 150psi	RTR-111C-334; CM-B4IF-66
8" Flanges, 150psi	RTR-111C-335; CM-B4IF-66
10" - 12" Flanges, 150psi	RTR-111C-336; CM-B4IF-66
14" - 24" Flanges, 150psi	RTR-111C-337; CM-B4IF-66
All materials are contact molded (closest definition to filament wound in D4024), epoxy vinyl ester resin, integrally molded flange. The grade epoxy is interpreted to include epoxy vinyl esters.	

ASTM D2310 / D2996 Pipe Codes

2" - 3" Pipe	RTRP-11FT1-1112
4" Pipe	RTRP-11FT1-1113
6" Pipe	RTRP-11FT1-1114
8" and larger Pipe	RTRP-11FT1-1116
All materials are filament wound, epoxy vinyl ester resin, reinforced liner, HDB of > 5,000psi for joints, > 10,000psi for pipe (axial loads included). Short term hoop strength > 10,000psi; long. tensile strength > 8,000psi; Long. tensile modulus > 1,000,000psi; stiffness factor varies with pipe size. The grade epoxy is interpreted to include epoxy vinyl esters. Replace 'T' with 'Q' for the HDB rating of joints.	

ASTM F1173 / ISO15840 Codes

Type I, Resin 2, Class B, Rating Method 1

ASTM D5685 Fittings Codes

--

Other Properties

Density (lb/cu in.)	0.06
Shear Modulus (psi)	1,400,000
Thermal Expansion Coefficient (in./in./F)	0.00001
Thermal Conductivity (BTU-in./ft^2-hr-F)	1.3
Minor Poisson's Ratio, $\nu_{min} = \nu_{ha}$	0.55
Major Poisson's Ratio, $E_a/E_h * \nu_{ha} = \nu_{ah}$	0.35
Hazen Williams Coefficient	150
Specific Roughness (in.)	0.0002

ASTM D5685 Fittings Codes

2" - 24" Fittings, 150psi	RTRF 52E4D
Contact molded fittings, epoxy vinyl ester resin, reinforced liner, butt & strap joint, 150psig rating	

Notes:
 1. Axial flexural is also termed bending; hoop flexural is also termed circumferential.
 2. Blank areas are Not Recommended.

**Table 110FW.E3M.1A (Metric)
(Series 110FW)
Mechanical Specifications**

Temp (C)	Pipe Strengths (MPa)					Pipe Moduli (GPa)				
	Axial Tensile	Hoop Tensile	Axial Flex.	Hoop Flex.	Axial Comp.	Axial Tensile	Hoop Tensile	Axial Flex.	Hoop Flex.	Axial Comp.
Ambient	57.9	182.0	115.8	N/A	124.1	9.7	15.2	9.7	15.2	10.3
65.6	57.9	182.0	115.8	N/A	124.1	9.7	15.2	9.7	15.2	10.3
79.4	56.5	177.5	112.9	N/A	121.0	9.4	14.8	9.4	14.8	10.1
93.3	55.0	172.9	110.0	N/A	117.9	9.2	14.4	9.2	14.4	9.8
107.2	53.6	168.4	107.1	N/A	114.8	8.9	14.0	8.9	14.0	9.6
121.1	52.1	163.8	104.3	N/A	111.7	8.7	13.7	8.7	13.7	9.3

ASTM D4024 / D5421 Flange Codes

2" - 6" Flanges, 150psi	RTR-111C-334; CM-B4IF-66
8" Flanges, 150psi	RTR-111C-335; CM-B4IF-66
10" - 12" Flanges, 150psi	RTR-111C-336; CM-B4IF-66
14" - 24" Flanges, 150psi	RTR-111C-337; CM-B4IF-66
All materials are contact molded (closest definition to filament wound in D4024), epoxy vinyl ester resin, integrally molded flange. The grade epoxy is interpreted to include epoxy vinyl esters.	

ASTM D2310 / D2996 Pipe Codes

2" - 3" Pipe	RTRP-11FT1-1112
4" Pipe	RTRP-11FT1-1113
6" Pipe	RTRP-11FT1-1114
8" and larger Pipe	RTRP-11FT1-1116
All materials are filament wound, epoxy vinyl ester resin, reinforced liner, HDB of > 5,000psi for joints, > 10,000psi for pipe (axial loads included). Short term hoop strength > 10,000psi; long. tensile strength > 8,000psi; Long. tensile modulus > 1,000,000psi; stiffness factor varies with pipe size. The grade epoxy is interpreted to include epoxy vinyl esters. Replace 'T' with 'Q' for the HDB rating of joints.	

ASTM F1173 / ISO15840 Codes

Type I, Resin 2, Class B, Rating Method 1

ASTM D5685 Fittings Codes

--

Other Properties

Density (g/cu cm)	1.7
Shear Modulus (GPa)	9.7
Thermal Expansion Coefficient (mm/mm/C)	0.000018
Thermal Conductivity (W-cm/cm^2-C)	0.0019
Minor Poisson's Ratio, $\nu_{min} = \nu_{ha}$	0.55
Major Poisson's Ratio, $E_a/E_h * \nu_{ha} = \nu_{ah}$	0.35
Hazen Williams Coefficient	150
Specific Roughness (cm)	0.0005

ASTM D5685 Fittings Codes

2" - 24" Fittings, 150psi	RTRF 52E4D
Contact molded fittings, epoxy vinyl ester resin, reinforced liner, butt & strap joint, 150psig rating	

Notes:
 1. Axial flexural is also termed bending; hoop flexural is also termed circumferential.
 2. Blank areas are Not Recommended.

**Table 110FW.E3.5A
(Series 110FW)
Stress Analysis Data**

Material Properties

C_t	0.000010 in./in./F	0.000018 mm/mm/C
$E_a = E_x$	1,400,000 psi	9.7 GPa
$\nu_{min} = \nu_{ha}$	0.55	0.55
E_h	2,200,000 psi	15.2 GPa
rho	0.060 lb/in. ³	1.7 g/cm ³
$E_a/E_h * \nu_{ha} = \nu_{ah}$	0.35	0.35

BS7159 Data

SH, $\epsilon_d * E_a$	2,520 psi	17.38 MPa
	(based on 0.0018 design strain)	
E_h/E_a	1.57	1.57
K	Mean temperature change multiplier, 0.85 for liquids, 0.8 for gases, 1.0 for amb. temp changes.	
Kn	Fatigue factor, 1.0 for static applications	

D	tr,min
1	0.25"
1.5	0.25"
2	0.25"
3	0.25"
4	0.25"
6	0.31"
8	0.38"
10	0.44"
12	0.50"
14	0.56"
16	0.63"
18	0.69"
20	0.75"
24	0.88"

D	tr,min
25	6.4mm
40	6.4mm
50	6.4mm
80	6.4mm
100	6.4mm
150	7.9mm
200	9.5mm
250	11.1mm
300	12.7mm
350	14.3mm
400	15.9mm
450	17.5mm
500	19.1mm
600	22.2mm

**Table 110FW.E3.4A
(110FW)**

ISO 14692 Part 3 - Annex D Calculations

Stress Intensification Factors (SIFs), Flexibility Factors (Kappa), Pressure Stress Multipliers (PSMs)
(BS7159, Type 2 Laminate, 0.0015 design strain)

Size (in.)	Series 110FW, 110FW-C						
	Flexibility Factor	Elbows			Tees		
		Axial bending SIF		Hoop bending SIF		SIF	PSM
		In-plane	Out-of-plane	In-plane	Out-of-plane		
2	1.3	1.1	1.2	1.9	1.7	1.1	1.0
3	1.9	1.5	1.6	2.5	2.2	1.3	1.0
4	2.0	1.5	1.6	2.5	2.3	1.5	1.0
6	2.5	1.7	1.8	2.5	2.5	1.7	1.0
8	2.8	1.9	2.0	2.5	2.5	1.7	1.0
10	3.0	2.0	2.1	2.5	2.5	1.8	1.0
12	3.0	2.0	2.2	2.5	2.5	1.7	1.0
14	3.0	2.1	2.2	2.5	2.5	2.0	1.0
16	3.0	2.1	2.3	2.5	2.5	1.9	1.0
18	3.0	2.2	2.3	2.5	2.5	2.0	1.0
20	3.0	2.1	2.3	2.5	2.5	2.1	1.0
24	3.0	2.2	2.3	2.5	2.5	2.1	1.0
30	3.0	2.5	2.5	2.5	2.5	2.3	1.0
36	3.0	2.5	2.5	2.5	2.5	2.3	1.0
42	3.0	2.5	2.5	2.5	2.5	2.3	1.0
48	3.0	2.5	2.5	2.5	2.5	2.3	1.0

Note: Tees that are qualified according to ISO14692 have a PSM of 1.0. Tees that are not qualified will typically have PSMs ranging from 1.8 to 3.0. Reducing tees will have slightly different SIFs than tees; however, it is acceptable to use the same values as the same-size tees. e.g., a 6"x2" reducing tee or outlet would have the same SIF as a 6" tee.