

Rev A - Oct-27-2008

Series Specifications 20JF16.E6 (20JF16)

(also includes Series 20JF16-C)

**Table 20JF16.E6.6C  
 (Series 20JF16)  
 Support Spacing (ft)**

(Limited by Bending Stress, Deflection of 0.50 in. over 3 spans, and Max. Spacing of 30.0 ft)

(See notes for information on what value of bending stress to use)

Size in.	Rating psi	500 psi	1000 psi	1500 psi	500 psi	1000 psi	1500 psi	500 psi	1000 psi	1500 psi
		SG = 0.85	SG = 0.85	SG = 0.85	SG = 1.0	SG = 1.0	SG = 1.0	SG = 1.15	SG = 1.15	SG = 1.15
0.50	232	5.8	8.2	9.0	5.8	8.2	8.9	5.7	8.1	8.9
0.75	232	6.7	9.4	10.0	6.6	9.3	9.9	6.6	9.3	9.8
1.00	232	7.4	10.5	11.0	7.3	10.4	10.7	7.3	10.3	10.6
1.50	232	8.7	12.3	12.6	8.5	12.1	12.2	8.4	11.9	11.9
2.00	232	9.7	13.7	14.1	9.5	13.4	13.4	9.3	12.9	12.9
2.50	232	10.5	14.9	15.3	10.3	14.5	14.5	10.0	13.9	13.9
3.00	232	11.2	15.8	16.5	10.9	15.4	15.4	10.6	14.6	14.6
4.00	232	12.3	17.4	18.5	11.9	16.8	16.9	11.5	16.0	16.0
5.00	232	13.1	18.5	18.5	12.6	16.9	16.9	12.1	16.0	16.0
6.00	232	13.7	19.4	21.7	13.1	18.6	19.3	12.6	17.8	18.0
8.00	232	14.6	20.7	24.3	13.9	19.7	21.2	13.3	18.8	19.5
10.00	232	15.3	21.6	26.4	14.5	20.4	22.7	13.8	19.5	20.8
12.00	232	15.7	22.2	27.2	14.9	21.0	23.9	14.1	20.0	21.9
14.00	232	16.8	23.8	29.1	15.8	22.4	25.7	15.0	21.3	23.5
16.00	232	18.2	25.8	30.0	17.2	24.3	27.7	16.3	23.0	25.2
18.00	232	19.6	27.7	30.0	18.4	26.1	29.5	17.5	24.7	26.9
20.00	232	20.8	29.5	30.0	19.6	27.7	30.0	18.6	26.3	28.4
24.00	232	23.1	30.0	30.0	21.8	30.0	30.0	20.6	29.1	30.0
30.00										
36.00										
42.00										
48.00										
54.00										
60.00										
66.00										
72.00										

Notes: Normally, we recommend 1000psi (6.9MPa) for an allowable bending stress due to support spacing, however, this value can range from 500psi (3.5MPa) to 1500psi (13.4MPa), depending upon the other axial & bending stresses in the system. At design temperatures of 200F (93c) or more, 500psi (3.5MPa) may be needed. At very low pressures and temperatures, 1500psi (13.4MPa) may be satisfactory.  
 For seawater, multiply the support spacings for SG=1.0 by 0.986 (i.e., the support spacings for seawater are approximately 98.6% of the values for SG=1.0 (water)).

Rev A - Oct-27-2008

Series Specifications 20JF16.E6 (20JF16)

(also includes Series 20JF16-C)

**Table 20JF16.E6M.6C (Metric)  
 (Series 20JF16)**

**Support Spacing (m)**

(Limited by Bending Stress, Deflection of 0.50 in. over 3 spans, and Max. Spacing of 30.0 ft)

(See notes for information on what value of bending stress to use)

Size mm	Rating bar	3.4 MPa 6.8 MPa 10.3 MPa			3.4 MPa 6.8 MPa 10.3 MPa			3.4 MPa 6.8 MPa 10.3 MPa		
		SG = 0.85	SG = 0.85	SG = 0.85	SG = 1.0	SG = 1.0	SG = 1.0	SG = 1.15	SG = 1.15	SG = 1.15
13	16	1.8	2.5	2.7	1.7	2.5	2.7	1.7	2.5	2.7
19	16	2.0	2.8	3.1	2.0	2.8	3.0	2.0	2.8	3.0
25	16	2.2	3.2	3.3	2.2	3.1	3.3	2.2	3.1	3.2
38	16	2.6	3.7	3.9	2.6	3.7	3.7	2.6	3.6	3.6
51	16	2.9	4.1	4.3	2.9	4.1	4.1	2.8	3.9	3.9
64	16	3.2	4.5	4.7	3.1	4.4	4.4	3.0	4.2	4.2
76	16	3.4	4.8	5.0	3.3	4.7	4.7	3.2	4.5	4.5
102	16	3.7	5.3	5.6	3.6	5.1	5.2	3.5	4.9	4.9
127	16	4.0	5.6	5.6	3.8	5.2	5.2	3.7	4.9	4.9
152	16	4.1	5.9	6.6	4.0	5.6	5.9	3.8	5.4	5.5
203	16	4.4	6.3	7.4	4.2	6.0	6.4	4.0	5.7	6.0
254	16	4.6	6.5	8.0	4.4	6.2	6.9	4.2	5.9	6.3
305	16	4.8	6.7	8.3	4.5	6.4	7.3	4.3	6.0	6.7
356	16	5.1	7.2	8.9	4.8	6.8	7.8	4.5	6.4	7.2
406	16	5.5	7.8	9.0	5.2	7.4	8.4	4.9	7.0	7.7
457	16	5.9	8.4	9.0	5.6	7.9	9.0	5.3	7.5	8.2
508	16	6.3	8.9	9.0	5.9	8.4	9.0	5.6	8.0	8.7
610	16	7.0	9.0	9.0	6.6	9.0	9.0	6.2	8.8	9.0
762										
914										
1067										
1219										
1372										
1524										
1676										
1829										

Notes: Normally, we recommend 1000psi (6.9MPa) for an allowable bending stress due to support spacing, however, this value can range from 500psi (3.5MPa) to 1500psi (13.4MPa), depending upon the other axial & bending stresses in the system. At design temperatures of 200F (93c) or more, 500psi (3.5MPa) may be needed. At very low pressures and temperatures, 1500psi (13.4MPa) may be satisfactory.

For seawater, multiply the support spacings for SG=1.0 by 0.986 (i.e., the support spacings for seawater are approximately 98.6% of the values for SG=1.0 (water)).